

Composizione chimica (EN1774)	ZAMA 2 ZL2/ZL0430/ZnAl4Cu3	ZAMA 3 ZL3/ZL0400/ZnAl4	ZAMA 5 ZL5/ZL0410/ZnAl4Cu1
Al	3.8-4.2	3.8-4.2	3.8-4.2
Cu	2.7-3.3	≤ 0.03	0.7-1.1
Mg	0.035-0.06	0.035-0.06	0.035-0.06
Pb	≤ 0.003	≤ 0.003	≤ 0.003
Fe	≤ 0.020	≤ 0.020	≤ 0.020
Cd	≤ 0.003	≤ 0.003	≤ 0.003
Sn	≤ 0.001	≤ 0.001	≤ 0.001
Si	≤ 0.02	≤ 0.02	≤ 0.02
Ni	≤ 0.001	≤ 0.001	≤ 0.001
Standard			
EN1774	ZL2/ZL0430/ZnAl4Cu3	ZL3/ZL0400/ZnAl4	ZL5/ZL0410/ZnAl4Cu1
ISO 301			
AS1881		Zn Al 4	Zn Al 4 Cu 1
JIS H2201		Zn Al 4	Zn Al 4 Cu 1